



# SABA Primer 760

UV blackout primer

## Description

SABA Primer 760 is a 1-component black primer for the additional UV protection of bonded PMMA, polycarbonate (PC) and glass windows.

## Field of application

The marine and transport sectors. SABA Primer 760 is suitable for the additional UV protection of bonded PMMA, polycarbonate (PC) and glass windows if there is no ceramic or silkscreen border present for UV protection.

## Advantages

- a deep black colour
- offers excellent protection against UV
- no stress corrosion or other degradation of the polycarbonate (PC) or polymethylmethacrylate (PMMA)

## Method of use

For instructions for use, see the relevant info sheets on [www.saba.nl](http://www.saba.nl)

Before opening the bottle, shake well for at least 60 seconds.

Close the packaging as soon as possible after use; this has a positive effect on the processing properties and the shelf life of the product.

## Technical data

<b>Basis</b>	isocyanides
<b>Viscosity at 23 °C</b> (EN 12092)	ca. 15 mPa.s
<b>Density at 23 °C</b> (EN ISO 2811-2)	approx. 930 kg/m <sup>3</sup>
<b>Solids content</b>	approx. 12 %
<b>Open time</b>	10 minutes to 24 hours
<b>Coverage</b>	approx. 100 g/m <sup>2</sup>
<b>Working temperature</b>	min. + 5 °C to max. + 35 °C
<b>Storage temperature</b>	min. + 5 °C to max. + 25 °C
<b>Temperature resistance</b>	min. -40 °C to max. + 120 °C

## Order information

<b>Packaging</b>	aluminium bottle with resealable lid
<b>Contents</b>	125 ml (contains 12 items)
<b>Colour</b>	black
<b>Article no.</b>	100871 ZCO
<b>Shelf life</b>	9 months (in unopened packaging)

*Other packaging on request. The shelf life may vary for large packaging.*

## Safety recommendations

For more information about safety, see the relevant SABA safety data sheet.