

# SABA Activator 9400

bonding promotor

## **Description**

SABA Activator 9400 is a 1-component bonding promotor for pre-treating and cleaning of various surfaces.

## Field of application

The marine, transport, building and industry sectors. SABA Activator 9400 is very suitable as a bonding promotor for the pretreatment of porous and non-porous surfaces, metals and plastics.

# **Advantages**

- · fast drying time
- free of isocyanates
- no spot or stain formation
- clean and activate in one action (with slight pollution)

#### **Method of use**

If there is extensive pollution, the substrates should be cleaned in advance with SABA Cleaner 48.

For further instructions for use, see the relevant info sheets on www.saba.nl

Close the packaging as soon as possible after use; this has a positive effect on the processing properties and the shelf life of the product.

#### **Technical data**

Basis	silan
Viscosity at 23 °C (EN 12092)	approx. 10 mPa.s
Density (EN ISO 2811-2)	approx. 820 kg/m <sup>3</sup>
Solids content	approx. 1 %
Flashpoint	approx. + 12 °C
Solvents	mixture of alcohols
Open time	10 minutes to 24 hours
Coverage	approx. 100 g/m <sup>2</sup>
Working temperature	min. + 5 °C to max. + 35 °C
Storage temperature	min. + 5 °C to max. + 35 °C
Temperature resistance	min 40 °C to max. + 120 °C

### **Order information**

Packaging	can with resealable lid
Contents	1 litre (contains 12 items)
Colour	transparent
Article no.	100326 DIW
Shelf life	12 months (in unopened packaging)

Other packaging on request. The shelf life may vary for large packaging.

# **Safety recommendations**

For more information about safety, see the relevant SABA safety data sheet.

SABA Dinxperlo BV

Industriestrant 3 NL-7091 DC Dinxperlo PO Box 3 NL-7090 AA Dinxperlo T+31 (0) 315 658999 F+31 (0) 315 653989 E info@saba.nl www.saba.nl

Our recommendations and instructions for use are based on the present status of know-how and technique. Clients and users should evaluate our products by themselves, with regard to utilization and requirements of their own choice. We shall take no responsibility in case our products are not being used subject to our recommendations and/or instructions for use. Furthermore, General Terms and Conditions of SABA Dinxperlo BV, will apply to our recommendations, instructions for use and the delivery of our products.