

Sabatack 790

fast bonding and sealing

Description

Sabatack 790 is a fast-acting, high-strength 1-component, elastic, humidity-curing, MS polymer-based construction adhesive and sealant. Its primary use is bonding with fast handling, high green strength (high viscosity) and very high tensile strength. Its secondary use is sealing seams, overlaps and joints. Sabatack 790 has a high viscosity and is high strength elasticity.

Field of application

Industrial and hand-made vehicle and coachwork construction, marine, ventilation and air conditioning, electro-technology, equipment assembly, metal and tin processing, plastics technology, civil & environmental engineering and building & construction. For the elastic bonding of frames, profiles, plates etc. Also for sealing seams, overlaps, joints and cracks. Suitable for interior and exterior use. Fast sealing directly before painting.

Advantages

- fast curing and drying, fast accumulation of strength and very high end strength
- adhesion without primer, hardly any shrinkage
- can be painted wet-on-wet
- no blistering, almost odourless
- free from solvents, isocyanates and silicones
- UV- stable, high temperature resistance
- certificates: Wheelmark (164.106/1121/WCL MED0328)



Method of use

For instructions for use, repaintability and pre-treatment, see the relevant info sheets at www.saba.nl

Technical data

Basis	MS polymer, humidity-curing
Density (EN 542)	approx. 1.380 kg/m ³
Solids content	approx. 100%
Skin time (23 °C, 50% RLV)	approx. 8 minutes
Open time (23 °C, 50% RLV)	approx. 10 minutes
Tack free (23 °C, 50% RLV)	after approx. 4 hours
Cure rate (23 °C, 50% RLV)	approx. 4 mm/24 hrs
Hardness Shore A (EN ISO 868)	approx. 64
Volume alteration (EN ISO 10563)	approx. 5%
Modulus at 100 % (ISO 37/DIN 53504)	approx. 2.0 N/mm ²
Tensile strength (ISO 37/DIN 53504)	approx. 3.5 N/mm ²
Elongation at break (ISO 37/DIN 53504)	approx. 250%
Shear strength (ISO 4587)	approx. 2.3 N/mm ²
Working temperature	min. +5 °C to max. +35 °C
Storage temperature	min. +5 °C to max. +25 °C
Temperature resistance	min. -40 °C to max. +120 °C
Short temperature resistance	max. +180 °C (30 minutes)

Order information

Packaging	cartridge	sausage
Contents	290 ml (contains 24 items)	600 ml (contains 15 items)
Colour	black (similar to RAL 9011)	white (similar to RAL 9003) black (similar to RAL 9011)
Article No.	100681 ABX	100749 AAL 100681 AAL
Shelf life	18 months (in unopened packaging)	15 months (in unopened packaging)

Other packaging and colours on request. The shelf life may vary for large packaging.

Safety recommendations

For more information about safety, see the relevant SABA safety data sheet.

SABA Dinxperlo BV

Industriestraat 3 NL-7091 DC Dinxperlo PO Box 3 NL-7090 AA Dinxperlo T+31 (0) 315 65 89 99 F+31 (0) 315 65 89 89 E info@saba.nl www.saba.nl

Our recommendations and instructions for use are based on the present status of know-how and technique. Clients and users should evaluate our products by themselves, with regard to utilization and requirements of their own choice. We shall take no responsibility in case our products are not being used subject to our recommendations and/or instructions for use. Furthermore, General Terms and Conditions of SABA Dinxperlo BV, will apply to our recommendations, instructions for use and the delivery of our products.

Version: 2011-01-01, replaces all previous versions

Page 1 of 1